



Technical Bulletin

2400 Boston Street, Suite 200, Baltimore, Maryland 21224
Phone: 410-675-2100 or 800-543-3840

Revised: 3/8/02

DAP® KWIK SEAL® Tub and Tile Adhesive Caulk Clear

- Bonds & seals
- Cured caulk is mildew resistant
- Easy water clean-up

Packaging: 5.5 fl. oz. (162 ml)
Color: Clear
UPC Number: 18008, 18016, 18040, 18041, 35032, 35030, 71055

Company Identification:

Manufacturer: DAP Inc., 2400 Boston St., Baltimore, Maryland 21224
Usage Information: DAP HELPLINE: 888-DAP-TIPS, 9:00 am to 7:00 pm EST.
Order Information: 800-327-3339
Fax Number: 410-534-2650
Also, visit the DAP website at www.dap.com.

Product Description:

KWIK SEAL® Tub & Tile Adhesive is an easy-to-use, multi-purpose adhesive caulk ideal for caulking and sealing in the bathroom and kitchen. It bonds like a glue and seals like a caulk. It is specially formulated to provide a watertight seal around tubs, sinks, showers and countertops. Cured caulk is mildew resistant. It offers excellent adhesion, flexibility and durability. It tools easily and dries tack free in 15 minutes. Excellent for areas subject to water contact and high humidity. Dried surface cleans easily and is paintable with either latex or oil-based paint. Resists abrasive chemicals. Easy water clean-up.

Suggested Uses:

Ideal for caulking and Sealing:

- Tubs
- Sinks
- Showers
- Countertops
- Other cracks and joints
- Backsplashes
- Vanities
- Fixtures
- Loose Tiles

Adheres To:

- Ceramic/Plastic Tile
- Glass
- Porcelain
- Fiberglass
- Wood
- Metal
- Plaster
- Drywall

Performance Characteristics:

- Cured caulk is mildew resistant.
- Caulk applies white and dries clear in 7-14 days (longer in cool or humid conditions).

- Caulk must be clear before painting with latex or oil-based paints.
- Product should not be applied where a silicone was previously applied.
- Water clean-up
- Provides a watertight seal.
- Resists cracking, crumbling and shrinking.

Surface Preparation & Application:

- Surface must be clean, dry and free of all old caulk, dirt, dust and grease. Rubbing alcohol is recommended for removing soap film and soil.
- Remove cap (from tube). Cut nozzle at 45° angle to desired bead size. Load into caulking gun if using the 10.1 oz cartridge.
- Joint width should not exceed 3/8". If joint depth exceeds 3/8", use backer rod material.
- Fill gap with caulk, pushing caulk ahead of nozzle.
- For a neat finish, smooth bead of caulk with finishing tool.
- Clean up excess caulk with a damp cloth before it skins over (15 minutes).
- Reseal tube for future use.

For Best Results:

- Caulk in temperatures above 40°F.
- Do not use for below waterline applications. Do not apply product under shower door track or in closed applications.
- Allow to dry and fully cure for at least 36 hours before exposing to water and moisture.
- Store caulk away from extreme heat or cold.

Physical & Chemical Characteristics:

Tooling Time:	10 Minutes
Tack Free Time:	15 Minutes
Paintability:	Yes
Odor:	Very Mild
Consistency:	Smooth and Creamy
Vehicle:	Latex Polymer
Volatile:	Water
Flash Point:	None
Filler:	Calcium Carbonate
Solids:	68 ± 1% by weight
Weight per Gallon:	11.81 lbs.
Temperature Service Range:	-20°F to 150°F
Temperature Application Range:	40°F to 100°F
Freeze Thaw Stability:	Passes 5 Cycles 0°F (1 cycle = 16 hrs. @ 0°F, 8 hrs. @ 70°F)
Applications:	Interior
Shelf Life:	12 Months
Coverage:	5.5 fluid ounces: 30 linear ft. at a 3/16" diameter bead or 2 bathtubs
MSDS No:	77120

Clean Up:

Clean up excess caulk with a damp cloth before it skins over (15 minutes). Dried material must be cut or scraped away.

Safety:

See product label or Material Safety Data Sheet for safety information. You can request an MSDS sheet by calling 888-DAP-TIPS or by visiting our website at www.dap.com.

Warranty Information:

If not satisfied with product performance when used as directed, return used container and sales receipt to DAP Inc., Technical Customer Service, 2400 Boston St., Baltimore, MD, 21224, for product replacement, or at DAP's discretion, sales price refund. DAP will not be liable for incidental or consequential damage.

