# DAP® TOUCH n' SEAL® 1.75 PCF HVAC ICC Spray Foam— Cream

#### PRODUCT DESCRIPTION

**DAP® Touch n' Seal ® 1.75 PCF HVAC ICC Spray Foam** is a two-component foam formula, available in a variety of low-pressure dispensing units. When used according to manufacturer's directions, 1.75 PCF ICC provides closed cell rigid polyurethane foam with ASTM E-84 Class A fire resistance. The system complies with IBC, IRC, and IECC as supported by ICC Evaluation Services listing ESR-3052.



PACKAGING	Case	COLOR	UPC
Foam Kit 200	1	Cream	7565021044
Foam Kit 600	1	Cream	7565021039
CP-750	1	Cream	7565021038
Constant Pressure			





### **TECHNICAL DATA SHEET**

2400 Boston Street |Suite 200 | Baltimore, MD | 21224

#### **KEY FEATURES & BENEFITS**

- Low-pressure, closed cell, medium density spray foam
- Saves energy and increases comfort by reducing drafts
- No shaking or pre-mixing required
- Cured foam does not shrink or settle
- Dries in 60 seconds
- Closed cell structure
- Reduces vibration and sound transmission.
- Low-odor formulation
- Easy to transport
- Low maintenance
- Increases structural strength
- 15 month shelf life

#### **SUGGESTED USES**

#### **USE TO COVER, FILL AND SEAL:**

- Ducts
- Duct Connections
- Around Vents
- Crawlspaces

- Basements
- Foundation walls

#### FOR BEST RESULTS

- Apply in temperatures between 60°F- 90°F
- Chemical contents must be between 70°F 90°F before dispensing
- Surface temperatures should be between 60°F- 90°F
- Surface must be free of oil and dirt for adhesion
- Do not store at temperatures above 120°F (49°C)

#### **APPLICATION**

DIRECTIONS: Important – read all directions and cautions before use. Always wear gloves, eye protection and work clothes. Use drop cloths. Always refer to local building codes prior to use.

**Preparation / Application:** Please refer to Operating Instructions found inside the product packaging or call Customer Service at 888-DAP-TIPS. Surfaces to be sprayed must be dry, clean, and free of dust, dirt, grease, and other substances that may inhibit proper adhesion.



## **TECHNICAL DATA SHEET**

2400 Boston Street |Suite 200 | Baltimore, MD | 21224

**Clean-up:** If wet foam contacts skin, clean immediately with a dry rag – do not use water – water accelerates curing. Cured foam must be removed mechanically from surfaces. Uncured foam can be cleaned from most surfaces with Foam Cleaner or acetone. Do not attempt to remove cured solvents. If foam dries on skin, apply generous amounts of petroleum jelly, put on plastic gloves and wait 1 hour. With a clean cloth, firmly wipe off residue and repeat process if necessary. DO NOT use acetone or other solvents to remove product from skin.

**Storage & Disposal.** Keep container tightly closed in a cool, well-ventilated area. Store upright below 90° F (33°C). Do not expose containers to conditions that may damage, puncture, or burst the containers. Dispose of leftover material / containers in accordance with Federal, state, and local regulations. See SDS for more information.

TYPICAL PHYSICAL & CHEMICAL PROPERTIES			
Shelf Life	15 months; unopened container		
Tack Free Time	30 - 60 seconds		
Fully Cured	Approx. 1 hour		
Cuttable	5 minutes		
Fungi Resistance	Does not support growth		
ASTM D1621 Compressive Strength	31 psi (214 kPa)		
ASTM E-90 Sound Transmission Class	32 @ 1-1/2" (38mm)		
ASTM E-96 Water Vapor Transmission	1.77 perms @ 1" (25mm)		
ASTM E-283 Air Permeance	<.004 CFM / ft2 (<.02 L/s/m2)		
ASTM C518 R-Value – Aged (1" / 2")	6.2 / 12.4		
ASTM D-1622 Density (Core)	1.75 pcf (28.0 kg/m3)		
ASTM D2856 Closed Cell Content	>90%		
ASTM D1623 Tensile Strength	31 psi (214 kPa)		
International Residential Code	Compliant		
Underwriters Laboratory Listed	R14175		
Surface Burning Characteristics 2" thickness (Flame / Smoke)	15 / 350		
Yield Bd ft.* Foam Kit 200 Foam Kit 600 CP-750	200 600 750		

<sup>\*</sup>Theoretical yield is used as an industry standard to represent the size of two-component foam kits. The calculation is based upon ideal conditions, does not include blowing agent loss, and may vary according to application method or environmental factors.

#### **SAFETY**

2 100 Booton Guest Journ 200 | Bultimore, INB | 2 122 1

See product label or Safety Data Sheet (SDS) for health and safety information. You can request an SDS by visiting our website at dap.com or calling 888-DAP-TIPS.

#### **WARRANTY**

**LIMITED WARRANTY:** If the product fails to perform when used as directed, within one year from the date of purchase, call 888-DAP-TIPS, with your sales receipt and product container available, for replacement product or sales price refund. DAP Products Inc. will not be responsible for incidental or consequential damages.

#### **COMPANY IDENTIFICATION**

Manufacturer: DAP Products Inc., 2400 Boston Street, Baltimore, Maryland 21224

Usage Information: Call 888-DAP-TIPS or visit dap.com & click on "Ask the Expert"

Order Information: 800-327-3339 or orders@dap.com

Fax Number: 410-558-1068

Also, visit the DAP website at dap.com